



3874™

December 2008

PRODUCT DESCRIPTION

3874™ provides the following product characteristics:

Technology	Acrylic
Chemical Type	Acrylic ester
Appearance (uncured)	Light grey opaque fluid , No visible bubbles. Slight separation of filler acceptable ^{LMS}
Components	One component - requires no mixing
Viscosity	High, thixotropic
Cure	Activator
Application	Bonding


3874™ is a thermally conductive adhesive. When used with Activator 7387™, it cures rapidly to form a high strength, high modulus, thermoset acrylic polymer. Typical applications include bonding heat sinks to heat dissipating components such as BGAs in electronics applications. The thixotropic nature of 3874™ reduces the migration of liquid product after application to the substrate.

TYPICAL PROPERTIES OF UNCURED MATERIAL

- Specific Gravity @ 25 °C 2.08
- Flash Point - See MSDS
- Viscosity, Brookfield - HBT, 25 °C, mPa·s (cP):
 - Spindle TB, speed 0.5 rpm, Helipath 800,000 to 1,800,000^{LMS}
 - Spindle TB, speed 5 rpm, Helipath 200,000 to 450,000^{LMS}

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The graph below shows the shear strength developed with time on grit blasted steel lap shears and tested according to ISO 4587. (Activator 7387™ applied to one surface).



TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 24 hours @ 70 °C, followed by 7 days @ 22 °C

Physical Properties:

Coefficient of Thermal Expansion, ISO 11359-2, K ⁻¹	76×10 ⁻⁶
Coefficient of Thermal Conductivity, ISO 8302, W/(m·K)	1.25
Glass Transition Temperature, °C	49
Shore Hardness, ISO 868, Durometer D	72
Elongation, at break, ISO 37, %	3.2

Initial @ 22 °C.

Electrical Properties:

Volume Resistivity, IEC 60093, Ω·cm	4.3×10 ¹⁴
Surface Resistivity, IEC 60093, Ω	3.8×10 ¹⁴
Dielectric Breakdown Strength, IEC 60243-1, kV/mm	23.6

After 1 week @ 85 °C / 85% RH

Electrical Properties:

Volume Resistivity, IEC 60093, Ω·cm	1.5×10 ¹⁴
Surface Resistivity, IEC 60093, Ω	2.6×10 ¹³
Dielectric Breakdown Strength, IEC 60243-1, kV/mm	3.5

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

After 24 hours @ 22 °C, Activator 7387™ on 1 side

Lap Shear Strength, ISO 4587:

Steel	N/mm ²	≥11.7 ^{LMS}
	(psi)	(≥1,695)
Aluminum	N/mm ²	≥7 ^{LMS}
	(psi)	(≥1,015)

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use:

1. For best performance bond surfaces should be clean and free from grease.
2. Apply Activator 7387™ to one of the bond surfaces and the adhesive to the other surface. Parts should be assembled immediately..
3. Excess adhesive can be wiped away with organic solvent.
4. Bond should be held clamped until adhesive has fixtured.
5. Product should be allowed to develop full strength before subjecting to any service loads (typically 24 to 72 hours after assembly, depending on bond gap, materials and ambient conditions).



Loctite Material Specification^{LMS}

LMS dated March 07, 2003. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\mu\text{m} / 25.4 = \text{mil}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.3